



Product information – Chintz 8003.--

Composition:	75% VI + 25% PA		
Weaving:	WARP: 42 ENDS WEFT: 29 PICKS		
Weight:	100 g/m ²		
Width:	153 cm		
Mechanical Properties:	Tensile strength Warp	460 N	ISO13934-1 2013
	Tensile strength Weft	420 N	ISO13934-1 2013
	Tear resistance (Elmendorf) (g) Warp.....	28 N	ISO13937-1 2000
	Tear resistance (Elmendorf) (g) Weft	23 N	ISO13937-1 2000
	Seam slippage Warp 80 N	2,0 MM	ISO13936-2 2004
	Seam slippage Warp 120 N	4,0 MM	ISO13936-2 2004
	Seam slippage Weft 80 N	3,0 MM	ISO13936-2 2004
	Seam slippage Weft 120 N	5,0 MM	ISO13936-2 2004
Dimensional Stability:	Shrinkage wash (40°C) Warp	-7 %	ISO 5077 2007
	Shrinkage wash (40°C) Weft	- 4,5 %	ISO 5077 2007
	Shrinkage at pressing Warp	- 3 %	DIN53894-2 1979
	Shrinkage at pressing Weft	- 2 %	DIN53894-2 1979
Colour Fastness:		Light Mid Dark	
	Colour fastness to wash 40°C	4/5 4 3/4	ISO 105/C06 2010
	Colour fastness to dry clean	4/5 4 3/4	ISO 105/D01 2010
	Colour fastness to water	4/5 4 3/4	ISO 105/E01 2013
	Colour fastness to dry rubbing	5 4 4	ISO 105/X12 2001
	Colour fastness to wet rubbing	4/5 3/4 3/4	ISO 105/X12 2001
	Colour fastness to light	4/5 4/5 4/5	ISO 105/B02 2014

Textile Care:

