



## Product information – Chintz water repellent 8108.01

Composition:	71% CV + 29% PA	
Weaving:	WARP: 42 ENDS WEFT: 26 PICKS	
Weight:	109 g/m <sup>2</sup>	
Width:	157 cm	
Technical Properties:	Seam slippage (mm) Warp/ Weft .....	< 6 Norm BS 3320 (8 kg)
	Seam slippage (mm) Weft / Warp .....	< 6 Norm BS 3320 (8 kg)
	Tear resistance (Elmendorf) (g) Warp .....	1920 UNE EN ISO 13937-1
	Tear resistance (Elmendorf) (g) Weft .....	1280 UNE EN ISO 13937-1
	Breaking strength (kg) Warp .....	68 UNE EN ISO 13937-1
	Breaking strength (kg) Weft .....	50 UNE EN ISO 13937-1
	Grain line.....	(2%) 3 cm standard test
Dimensional Stability:	Dimensional stability to steam ironing (%) Warp	<2 standard test (2 p)
	Dimensional stability to steam ironing (%) Weft	<2 standard test (2 p)
	Dimensional stability to water cleaning (%) Warp	3,5 standard test (30°C)
	Dimensional stability to water cleaning (%) Weft	4 standard test (30°C)
Colour Fastness:	Colour fastness to wash.....	3-4 ISO 105/C01 1978 (40°C)
	Colour fastness to water.....	3 ISO 105/E01 1978
	Colour fastness to acid sweat.....	3 ISO 105/E04 1978
	Colour fastness to alkali sweat.....	3 ISO 105/E04 1978
	Colour fastness to dry clean.....	4 ISO 105/D01 1978
	Colour fastness to dry rubbing.....	3-4 ISO 105/X12 1978
	Colour fastness to wet rubbing.....	3 ISO 105/X12 1978
	Colour fastness to chlorine.....	3 ISO 105/E03 1978

Textile Care:

