









TECHNICAL DATA

		8268
Structure		Plain 1 : 1
Composition (polyester)		100%
Weight - g/m2		100
Width - cm		300

FASTNESS PICTURE

		DYED	
ISO 6330:2012, ISO 5077:2007, ISO 3759:2011		Warp	Weft
Shrinkage at 40°C (%) after 2 dots ironing		-1.0	0
Color fastness to light (1-8)	ISO 105 B02:2014	Light colors	5 - 6
		Medium colors	5 - 6
		Dark colors	5
Color fastness to washing 40 °C (1-5)	ISO 105 C06:2010	Light colors	5
		Medium colors	5
		Dark colors	5
Color fastness to rubbing - dry (1-5)	ISO 105-X12 : 2001	Light colors	5
		Medium colors	5
		Dark colors	5
Color fastness to rubbing - wet (1-5)	ISO 105-X12 : 2001	Light colors	5
		Medium colors	5
		Dark colors	5
Washing instructions		Washing maxim temperature	30 °C
		Bleach	No
		Iron maxim temperature	120 °c
		Dry clean	Recommended
		Dry in the shade	Yes
		Tumble dry	No
		Spin	Soft

CUSTOMS CODE (HS)

551519

CERTIFICATES



Class I - App. 4

where applicable:

Revised September 2018