


8412 Laguna

GENERAL INFORMATION

Composition	100% PES
Weight g/m ²	350g
Weight g/Lm	497g
Width	142cm
Min. usable Width	138cm
Piece Length	35m
Tariff code	60053700

CLEANING INSTRUCTIONS



TECHNICAL DATE

• SHRINKAGE	40° WARP	0.25%		
	WEFT	1.4%		
• MARTINDALE ABRASION ISO12947-2 1998	END POINT	>100000		
	CHANGE IN COLOR	5 (6000 Cycles)		
• SEAM SLIPPAGE EN ISO 13936-2	WARP	2mm		
	WEFT	1mm		
• TEAR STRENGTH EN ISO 13937-3:2000	WARP	64.20N		
	WEFT	93.20N		
• TENSILE STRENGTH ISO 13934-1	WARP	615.32N	elongation	15.27%
	WEFT	335.35N	elongation	20.75%
• COLOUR FASTNESS EN ISO 105-X12	WARP DRY WARP	4/5		
	WET WEFT DRY	4		
	WEFT WET	4/5		
		4		
• COLOUR FASTNESS TO LIGHT EN ISO 105-B02	GRADE	Col 100: 4/5		
	GRADE	Col 101: 5		
	GRADE	Col 102: 4/5		
	GRADE	Col 103: 4/5		
	GRADE	Col 200: 4		
	GRADE	Col 201: 4/5		
	GRADE	Col 202: 4/5		
	GRADE	Col 203: 5		
	GRADE	Col 300: 4/5		
	GRADE	Col 301: 4		
	GRADE	Col 400: 4/5		
	GRADE	Col 401: 5		
	GRADE	Col 500: 4/5		
	GRADE	Col 501: 4/5		
	GRADE	Col 502: 3/4		
	GRADE	Col 503: 4		
GRADE	Col 504: 3/4			
GRADE	Col 600: 5			



8412 Laguna

GRADE	Col 601: 4/5
GRADE	Col 602: >5
GRADE	Col 603: 4/5
GRADE	Col 604: 4/5
GRADE	Col 606: 3/4
GRADE	Col 607: 4
GRADE	Col 609: 5
GRADE	Col 700: 5
GRADE	Col 701: 4
GRADE	Col 702: 5
GRADE	Col 703: 4/5
GRADE	Col 704: 4
GRADE	Col 706: 4
GRADE	Col 707: 6
GRADE	Col 800: 5
GRADE	Col 801: 4/5
GRADE	Col 802: 6
GRADE	Col 804: 4
GRADE	Col 900: 4
GRADE	Col 901: 3/4
GRADE	Col 902: 4/5
GRADE	Col 904: 6
GRADE	Col 905: 3/4
GRADE	Col 906: 6
GRADE	Col 907: 6+

- **PILLING ON MARTINDALE** 500 RUBS 5
ISO 12945-2:2000 1000 RUBS 5
2000 RUBS 5
5000 RUBS 5
- **PILLING TEST** GRADE 4/5
BS5811-1986