

COLLECTION : OLBIA

ARTICLE : 8439

### BASIC INFORMATION

Brand	VPF	Number of colour ways	40
Tariff item number	5407613000	MID	INDEEXP16
Country of origin	India	Characteristics	Texture
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Face in	Yes	Full roll diameter cm	16
Full roll diameter inch	6.3	Average piece length m	50
Minimum for special colour m	1000	Delivery time weeks special lab dip	2

### CARE AND USAGE

#### Care codes



Care code for bleaching

Do not bleach

#### Use codes

Curtains	Yes	Curtains and draperies	Yes
Upholstery	Yes	Bed covering	Yes
Accessories	Yes		

### ENVIRONMENTAL STANDARDS



STANDARD  
100  
0611045  
Centexbel

### FR STANDARDS

BS5852 source 0	Yes	CAL 117 Complies	Yes
FMVSS 302 Pass	Yes	NFPA 260	Yes
NFPA 701	Yes		

## FABRIC SPECIFICATIONS

Composition	100% Polyester	Average yarn number	35.18
Construction	67.72x28.31	Woven	Yes
Useable width cm	1.40	Useable width inch	55.12
Full width cm	142	Full width inch	55.9
Weight g/m <sup>2</sup>	273	Thickness mm	0.000
Colouring type	Piece dyed	Filament or staple	100% Filament
Textured or non textured	100% Not Textured		

### Treatment

No treatment Yes

### Type of finish

Stenter Yes

### Type of print or dye

Disperse Yes

### Weaving type

Jacquard Yes

## FABRIC TYPE

There are no technical details for this section.

## MECHANICAL PERFORMANCE

Martindale rubs	25,000	Colour fastness to light	5-6
Wyzenbeek double rubs	25,000	Pilling	4
Brush pilling	4	Wyzenbeek wire screen double rubs	6,000
Wyzenbeek cotton duck double rubs	25,000	Wyzenbeek cotton duck type heavy upholstery	Yes
Wyzenbeek wire screen light duty	Yes		
<b>Colour fastness to light - ISO 105-B02</b>			
Colour fastness to light	5-6		
<b>Colour fastness to water - ISO 105-E01</b>			
Colour fastness to water	5		
<b>Colour fastness to dry rub - ISO 105-X12</b>			
Colour fastness dry rub	4-5		
<b>Colour fastness to wet rub - ISO 105-X12</b>			
Colour fastness wet rub	4-5		
<b>Colour fastness to wear - ISO 12947-2</b>			
Colour fastness to wear	4		
<b>Tearing strength - ISO 13937-3</b>			
Tearing strength warp N	180	Tearing strength weft N	55
<b>Tensile strength - ISO 13934-1</b>			
Tensile strength warp N/5cm	1200	Tensile strength weft N/5cm	2000
<b>Elongation - ISO 13934-1</b>			
Elongation warp %	37	Elongation weft %	22.5
<b>Seam slippage - ISO 13936-2</b>			
Seam slippage warp mm	5	Seam slippage weft mm	5
<b>Dimensional stability (indicated in %) - ISO 3759</b>			
Dimensional change warp	0.02	Dimensional change warp after ironing with steam	0.00
Dimensional change warp after ironing without steam	0.00	Dimensional change weft	-0.08
Dimensional change weft after ironing with steam	0.40	Dimensional change weft after ironing without steam	0.33

## WASHABILITY

### Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-0.33	Dimensional change warp after ironing	-0.27
Dimensional change weft	-0.03	Dimensional change weft after ironing	0.00
Colour fastness ISO 105 C06	5		

### Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-1.40	Dimensional change warp after ironing	-1.20
Dimensional change weft	-0.23	Dimensional change weft after ironing	-0.20
Colour fastness ISO 105 C06	5		

### Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-1.03	Dimensional change warp after ironing	-0.07
Dimensional change weft	-0.10	Dimensional change weft after ironing	-0.07
Colour fastness ISO 105 D01	5		

## CONSTRUCTION

### Yarn 1

Warp Composition	100% Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Sizes	75/36/700 brt grey
Warp Threads per cm	67.72	Warp TPM	600

### Yarn 2

Weft Composition	100% Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Sizes	6Nm
Weft Threads per cm	1.97	Weft TPM	NA

### Yarn 3


Weft Composition	100% Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Sizes	400D
Weft Threads per cm	10.2	Weft TPM	NA

### Yarn 4

Weft Composition	100% Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Sizes	450D
Weft Threads per cm	12.2	Weft TPM	NA

### Yarn 5

Weft Composition	100% Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Sizes	6s
Weft Threads per cm	3.94	Weft TPM	NA



DOWNLOADS / CERTIFICATES

There are no technical details for this section.