

COLLECTION : WOODS

ARTICLE : 8441

BASIC INFORMATION

Brand	VPF	Number of colour ways	9
Tariff item number	5407930000	MID	TRTEXTRABU
Country of origin	Turkey	Characteristics	Jacquard
Vertical repeat cm	64.40	Vertical repeat inch	25.35
Horizontal repeat cm	29.20	Horizontal repeat inch	11.50
Face in	Yes	Full roll diameter cm	19
Full roll diameter inch	7.48	Average piece length m	50
Minimum for special colour m	1000	Delivery time weeks special lab dip	4

CARE AND USAGE

Care codes



Care code for bleaching

Do not bleach

Use codes

Curtains	Yes	Curtains and draperies	Yes
Bed covering	Yes	Accessories	Yes

ENVIRONMENTAL STANDARDS



FR STANDARDS

CAL 117 Complies	Yes	FMVSS 302 Pass	Yes
NFPA 260	Yes	NFPA 701	Yes

COLLECTION : WOODS

ARTICLE : 8441

FABRIC SPECIFICATIONS

Composition	100% Polyester	Average yarn number	65.2
Construction	80x34	Woven	Yes
Useable width cm	1.46	Useable width inch	57.48
Full width cm	148	Full width inch	58.27
Weight g/m ²	227	Thickness mm	0.000
Colouring type	Yarn dyed	Filament or staple	60% filament + 30% staple
Textured or non textured	65% textured + 35% not textured		

Treatment

No treatment Yes

Type of finish

Calender	Yes	Thermofixed	Yes
Washed	Yes		

Type of print or dye

Disperse Yes

Weaving type

Jacquard Yes

FABRIC TYPE

There are no technical details for this section.

COLLECTION : WOODS

ARTICLE : 8441

MECHANICAL PERFORMANCE

Martindale rubs	6,000	Colour fastness to light	4-5
Wyzenbeek double rubs	45,000	Pilling	3-4
Wyzenbeek wire screen double rubs	15,000	Wyzenbeek cotton duck double rubs	45,000
Wyzenbeek cotton duck type heavy upholstery	Yes	Wyzenbeek wire screen heavy duty	Yes
Colour fastness to light - ISO 105-B02			
Colour fastness to light	4-5		
Colour fastness to water - ISO 105-E01			
Colour fastness to water	5		
Colour fastness to dry rub - ISO 105-X12			
Colour fastness dry rub	4-5		
Colour fastness to wet rub - ISO 105-X12			
Colour fastness wet rub	4-5		
Colour fastness to wear - ISO 12947-2			
Colour fastness to wear	4-5		
Tearing strength - ISO 13937-3			
Tearing strength warp N	100	Tearing strength weft N	46
Tensile strength - ISO 13934-1			
Tensile strength warp N/5cm	1200	Tensile strength weft N/5cm	1800
Elongation - ISO 13934-1			
Elongation warp %	44.5	Elongation weft %	21.5
Seam slippage - ISO 13936-2			
Seam slippage warp mm	3	Seam slippage weft mm	4
Dimensional stability (indicated in %) - ISO 3759			
Dimensional change warp	-0.07	Dimensional change warp after ironing with steam	0.00
Dimensional change warp after ironing without steam	0.00	Dimensional change weft	0.00
Dimensional change weft after ironing with steam	0.00	Dimensional change weft after ironing without steam	-0.07

COLLECTION : WOODS

ARTICLE : 8441

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-0.07	Dimensional change warp after ironing	0.00
Dimensional change weft	0.03	Dimensional change weft after ironing	0.13
Colour fastness ISO 105 C06	5		

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-0.93	Dimensional change warp after ironing	-0.87
Dimensional change weft	-0.03	Dimensional change weft after ironing	-0.07
Colour fastness ISO 105 C06	5		

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-0.73	Dimensional change warp after ironing	-0.27
Dimensional change weft	-0.23	Dimensional change weft after ironing	-0.27
Colour fastness ISO 105 D01	5		

CONSTRUCTION

Yarn 1

Warp Composition	100% Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Textured	Yes
Warp Sizes	75 den	Warp Textured	Yes
Warp Threads per cm	80	Warp TPM	500

Yarn 2

Weft Composition	100% Polyester	Weft Is Not High Tenacity	Yes
Weft Is Staple	Yes	Weft Sizes	NE 12/1
Weft Threads per cm	34	Weft TPM	NA

Yarn 3

Weft Composition	100% Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Sizes	270 den
Weft Threads per cm	34	Weft TPM	100

[COLLECTION : WOODS](#)[ARTICLE : 8441](#)[DOWNLOADS / CERTIFICATES](#)

There are no technical details for this section.