

**PRODUCT INFORMATION SHEET**

**PVC RIGID FILM MAT**

Article / Artikel	RPVC4015201
Colour / Farbe	white / weisse
Thickness / Dicke	400 m

Parameter Parameter	Regulation Nomen	Methode Methode	Values Werte		Units Einheiten
Thicknesstolerance Dickentoleranz	EN 1849-2	Micrometer	400+/- 5%		my
Tensile stress at break Bruchspannung	EN ISO 527 - 3	70 mm/min	Longitudinal Längs	>56	MPa
			Transversal Quer	>54	
Tensile strain at break Bruchdehnung	EN ISO 527 - 3	70 mm/min	Longitudinal Längs	>13	%
			Transversal Quer	>4	
Shrinkage Schrumpf	DIN 53377	10 min.; + 80 °C	< -5		%



The foils should be stored in closed rooms in hanging or up-right standing position in their original package and without further application of pressure at a temperature of 10° up to 30°C. Heat radiation by exposure to sunlight and to heating/hot-air should generally be avoided. Relative humidity of the atmosphere may not exceed 70%. Influences other than typical for storerooms (like e.g. harming environmental gases or vapours) must not appear. Storage life 1 year

This values of the mechanical properties are for smooth or slightly embossed foils. Strong grain may show deviations.

This technical information sheet represents our latest state of knowledge and shall inform without obligation. The herein stated details do not release the manufacturer of our products from their own inspections and tests, which must correspond with the relevant national guidelines for its individual intended purpose. Especially it is the duty of the customer to control if the purchased product is suitable for its intended purpose.